



ELASTO**CRETE**

LIMITLESS CONCRETE

Sand Ratios For ElastoCrete (INTERIOR)

BASE MIX DESIGN:

ACS Marble Pro sand 50 lbs per kit
Medium 30 Grit Silica Sand 50 lbs per kit

MARBLE MIX DESIGN:

ACS Marble Pro sand 75 lbs per kit (recommend for countertops only)

ADD 3 LBS ICE OR WATER

Ice and water allows for optimal temperature of the mix design. Warm water can also be used if temperatures are colder. Best performance is achieved when liquid is between: 55-75 degrees F
13-25 C.

MIXING ORDER:

33.5 lbs Liquid + 3 lbs ice or water
Color Pigment
21 lbs Cement
ACS Marble Pro Sand
30 Grit Silica Sand

Sands can be purchased from ElastoCrete